

Appln No.: 10/605,671  
Amendment Dated: January 12, 2006  
Reply to Office Action of October 18, 2005

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (currently amended) A composition comprising:
  - (a) a bulk resin component comprising a polycarbonate resin;
  - (b) a polycarbonate-siloxane copolymer in an amount sufficient to provide an amount of siloxane of at least 3% by weight of the total composition; and
  - (c) a colorant composition comprising titanium dioxide having an organic coating, wherein the amount of titanium dioxide is from 1 to 2.5 % by weight of the total composition, and further comprising an antidrip agent, wherein the antidrip agent is styrene-acrylonitrile copolymer encapsulated polytetrafluoroethylene.
2. (original) The composition of claim 1, wherein the bulk resin component makes up at least 50% of the composition.
3. (original) The composition of claim 2, wherein the amount of titanium dioxide is from 1 to 1.5% by weight of the total composition.
4. (original) The composition of claim 3, further comprising a rubbery impact modifier.
5. (original) The composition of claim 4, wherein the rubbery impact modifier is selected from the group consisting of acrylic rubbers, ASA rubbers, diene rubbers, organosiloxane rubbers, EPDM rubbers, styrene-butadiene-styrene (SBS) or styrene-ethylene-butadiene-styrene (SEBS) rubbers, ABS rubbers, MBS rubbers and glycidyl ester impact modifiers, and mixtures thereof.
6. (original) The composition of claim 5, wherein the rubbery impact modifier is present in an amount of from 1 to 30% by weight.
- 7-8. (canceled)
9. (currently amended) The composition of claim 1 8, further comprising an effective flame-retarding amount of flame retardant.
10. (original) The composition of claim 9, wherein the flame retardant is a phosphate flame retardant.

Appln No.: 10/605,671  
Amendment Dated: January 12, 2006  
Reply to Office Action of October 18, 2005

11. (original) The composition of claim 10, wherein the phosphate flame retardant is bis-phenol A tetraphenyl diphosphate.

12. (original) The composition of claim 9, wherein the flame retardant is a sulfonate.

13. (original) The composition of claim 12, wherein the sulfonate is a perfluoroalkane sulfonate.

14. (original) The composition of claim 13, wherein the perfluoroalkane sulfonate is potassium perfluorobutane sulfonate.

15. (original) The composition of claim 3, wherein the organic coating comprises an organosiloxane.

16. (original) The composition of claim 15, wherein the amount of titanium dioxide is from 1 to 1.5% by weight of the total composition.

17. (currently amended) The composition of claim ~~16~~ 23, further comprising an effective flame-retarding amount of flame retardant.

18. (original) The composition of claim 17, wherein the flame retardant is a phosphate flame retardant.

19. (original) The composition of claim 18, wherein the phosphate flame retardant is bis-phenol A tetraphenyl diphosphate.

20. (original) The composition of claim 17, wherein the flame retardant is a sulfonate.

21. (original) The composition of claim 20, wherein the sulfonate is a perfluoroalkane sulfonate.

22. (original) The composition of claim 21, wherein the perfluoroalkane sulfonate is potassium perfluorobutane sulfonate.

23. (currently amended) A composition comprising:  
(a) a bulk resin component comprising a polycarbonate resin;  
(b) a polycarbonate-siloxane copolymer in an amount sufficient to provide an amount of siloxane of at least 3% by weight of the total composition; and

Appln No.: 10/605,671  
Amendment Dated: January 12, 2006  
Reply to Office Action of October 18, 2005

(c) a colorant composition comprising titanium dioxide having an organic coating, wherein the amount of titanium dioxide is from 1 to 2.5 % by weight of the total composition, wherein the bulk resin component makes up at least 50% of the composition and  
~~The composition of claim 15;~~ wherein the organic coating comprises a trimethylolpropanol.

24. (original) The composition of claim 23, wherein the bulk component further comprises a rubbery impact modifier.

25. (original) The composition of claim 24, wherein the rubbery impact modifier is selected from the group consisting of acrylic rubbers, ASA rubbers, diene rubbers, organosiloxane rubbers, EPDM rubbers, styrene-butadiene-styrene (SBS) or styrene-ethylene-butadiene-styrene (SEBS) rubbers, ABS rubbers, MBS rubbers and glycidyl ester impact modifiers, and mixtures thereof.

26. (original) The composition of claim 23, further comprising an effective flame-retarding amount of flame retardant.

27. (original) The composition of claim 2, wherein the organic coating comprises trimethylolpropanol.

28. (original) The composition of claim 27, wherein the amount of titanium dioxide is from 1 to 1.5% by weight of the total composition.

29-30 (canceled).

31. (currently amended) An article, having a wall thickness greater than a first thickness, said article being formed from a molding composition in accordance with claim 1 comprising:

- ~~(a) a bulk resin component comprising a polycarbonate resin;~~
- ~~(b) a polycarbonate-siloxane copolymer; and~~
- ~~(c) a colorant composition comprising titanium dioxide, wherein the titanium dioxide has an organic coating, and~~ the amount of polycarbonate-siloxane copolymer is selected such that molding composition achieves a V0 UL fire rating at the first thickness.

32. (canceled)

33. (currently amended) The article of claim 31 ~~32~~, wherein the first thickness is 1.6 mm, and the polycarbonate-siloxane copolymer is present in an amount sufficient to provide an amount of siloxane of at least 3% by weight of the total composition.

Appln No.: 10/605,671  
Amendment Dated: January 12, 2006  
Reply to Office Action of October 18, 2005

34. (currently amended) The article of claim 31 ~~32~~, wherein the organic coating comprises an organosiloxane.

35. (original) The article of claim 34, wherein the amount of titanium dioxide is from 1 to 1.5% by weight of the total composition.

36. (original) The article of claim 35, further comprising an effective flame-retarding amount of flame retardant.

37. (original) The article of claim 36, wherein the flame retardant is a phosphate flame retardant.

38. (original) The article of claim 37, wherein the phosphate flame retardant is bis-phenol A tetraphenyl diphosphate.

39. (original) The article of claim 36, wherein the flame retardant is a sulfonate.

40. (original) The article of claim 39, wherein the sulfonate is a perfluoroalkane sulfonate.

41. (original) The article of claim 40, wherein the perfluoroalkane sulfonate is potassium perfluorobutane sulfonate.

42. (original) The article of claim 34, wherein the organic coating comprises trimethylolpropanol.

43. (original) The article of claim 42, wherein the bulk component further comprises a rubbery impact modifier.

44. (original) The article of claim 43, wherein the rubbery impact modifier is selected from the group consisting of acrylic rubbers, ASA rubbers, diene rubbers, organosiloxane rubbers, EPDM rubbers, styrene-butadiene-styrene (SBS) or styrene-ethylene-butadiene-styrene (SEBS) rubbers, ABS rubbers, MBS rubbers and glycidyl ester impact modifiers, and mixtures thereof.

45. (original) The article of claim 42, further comprising an effective flame-retarding amount of flame retardant.

46-61. (canceled)

Appln No.: 10/605,671

Amendment Dated: January 12, 2006

Reply to Office Action of October 18, 2005

62. (new) An article, having a wall thickness greater than a first thickness, said article being formed from a molding composition in accordance with claim 23, wherein the amount of polycarbonate-siloxane copolymer is selected such that molding composition achieves a V0 UL fire rating at the first thickness.

63. (new) The article of claim 62, wherein the amount of titanium dioxide is from 1 to 1.5% by weight of the total composition.

64. (new) The article of claim 63, further comprising an effective flame-retarding amount of flame retardant.

65. (new) The article of claim 64, wherein the flame retardant is a phosphate flame retardant.

66. (new) The article of claim 65, wherein the phosphate flame retardant is bis-phenol A tetraphenyl diphosphate.

67. (new) The article of claim 64, wherein the flame retardant is a sulfonate.

68. (new) The article of claim 67, wherein the sulfonate is a perfluoroalkane sulfonate.

69. (new) The article of claim 68, wherein the perfluoroalkane sulfonate is potassium perfluorobutane sulfonate.

70. (new) The article of claim 62, wherein the bulk component further comprises a rubbery impact modifier.

71. (new) The article of claim 70, wherein the rubbery impact modifier is selected from the group consisting of acrylic rubbers, ASA rubbers, diene rubbers, organosiloxane rubbers, EPDM rubbers, styrene-butadiene-styrene (SBS) or styrene-ethylene-butadiene-styrene (SEBS) rubbers, ABS rubbers, MBS rubbers and glycidyl ester impact modifiers, and mixtures thereof.